

545-5120 Versaprime® 275 Pre-Cat Pigmented Primer

Product codes: 545-5120 White Primer	Viscosity	Zahn #2 signature cup 28-32 sec at 77°F
	Flash Point:	-4°F (-20°C)
	Density (lb/gal):	9.48
	Solid (% by weight):	43.8%
	Solid (% by volume):	27.7%
	Shelf Life (months):	3

Product Description:

Versaprime 275 is a one-component, high solids, pre-catalyzed lacquer used as a primer. This pigmented pre-catalyzed primer provides chemical resistance along with adhesion over all wood species. The coating is supplied at a ready to spray viscosity.

Uses:

Versaprime 275 is recommended for use as a primer for kitchen cabinets, office and household furniture as well as many other interior wood applications. It has good filling properties and hiding characteristics. Versaprime is a pure white primer with excellent sandability.

Environmental Data (as supplied):	VOC less exempt lb/gal:	<2.29
	VOC lb/gal:	<1.0
	VOC less exempt g/l:	
	VOC g/l:	
	VOC lb/lb Solid:	<0.25
	VHAPs lb/lb Solid:	<0.01

Note:

See individual compliance sheets for specific data

Application Data	Suggested Uses:	Wood Primer
	Mixing Ratio:	100 parts 545-5120 to 1.75 parts 873-1900 (as a post-cat)
	Suggested Uses:	8 hours
	Application Viscosity:	Zahn #2 signature cup 28 – 32 seconds
	Reducer:	800-5500
	Retarder:	N/A
	Clean-up Solvent:	800-5500
	Recommended Wet Film:	3 – 5 mils
	Coverage:	445 sq. ft/gal at 1 mil dry and at 100% transfer efficiency. Coverage will vary depending on method of application or coating thickness.
	Note:	N/A

Directions for use:**Surface Preparation:**

Substrate should be sanded using 120, 150 or 180 grit steared papers prior to coating. Primers, if used, should be sanded with 280/320 grit steared paper prior to being coated. When recoating the previous coat of Versaprime 275 must be sanded and the next coat applied within eight hours. Versaprime 275 cannot be used on metal, old oil or cellulose lacquers.

General Information:

Agitate material before use. Always mix Versaprime 275 while adding catalyst and reducers in the recommended mixing ratios. Versaprime 275 must be agitated thoroughly at all times to ensure product consistency.

Apply at 3 – 5 mils wet sanded substrate. Further coats may be applied after complete drying followed by sanding with 280/320 grit steared paper. The second and subsequent coats must be applied the same day as the previous coat is sanded.

Maximum film build of Versaprime 275 should not exceed 2 – 3 mils dry.

Maximum film build of total coating system must not exceed 4 mils dry.

Contact with metal surfaces should be avoided. Versaprime 275 must not be polluted with oil, varnish or the like and must not be sanded with steel wool between coats. Versaprime 275 must not be used and dried at temperatures below 64°F or relative humidity above 65%.

During the curing process, the coating must not be exposed to ammonia vapors. Ammonia cleaners should not be used for cleaning the finish surfaces. This may accelerate discoloration.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

	Room Temperature (20°C / 68°F)	Forced Drying Schedule (50°C / 122°F)
Tack Free Time:	5 - 8 minutes	Flash off before entering oven
Dry to Sand:	10 - 15 minutes	1 hour
Dry to Stack:	5 - 8 minutes	30 minutes

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111

Updated: 2024-05-18 01:00:36

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.