

825-5600 Promatch® Vivid Color Wipe SB Stain

| | | |
|--------------------------------|-----------------------------|---------------|
| Product codes: 825-5600 | Viscosity | N/A |
| | Flash Point: | -4 °F (-20°C) |
| | Density (lb/gal): | 6.9 |
| | Solid (% by weight): | 10% |
| | Solid (% by volume): | 6% |
| | Shelf Life (months): | 24 |

Product Description:

825-5600 is a wipe stain base formulated especially to be tinted with the Huls 844 colorants. Its unique solvent blend also gives the option of using permatone dyes or concentrated liquid dyes for the development of rich and deep colors.

Uses:

825-5600 offers a simple one step stain system with very good clarity and grain fill. Its ease of workability and good open time allows for uniform appearance on large pieces.

| | | |
|------------------------------------------|--------------------------------|--------|
| Environmental Data (as supplied): | VOC less exempt lb/gal: | <6.3 |
| | VOC lb/gal: | <6.3 |
| | VOC less exempt g/l: | |
| | VOC g/l: | |
| | VOC lb/lb Solid: | <8.9 |
| | VHAPs lb/lb Solid: | <0.005 |

Note:
N/A

| | | |
|-------------------------|-------------------------------|-------------------------------------|
| Application Data | Suggested Uses: | Wood Stain |
| | Mixing Ratio: | N/A |
| | Suggested Uses: | N/A |
| | Application Viscosity: | N/A |
| | Reducer: | No reduction required |
| | Retarder: | N/A |
| | Clean-up Solvent: | 800-5500 Acetone or lacquer thinner |
| | Recommended Wet Film: | N/A |
| | Coverage: | N/A |

Note:
N/A

Directions for use:

Surface Preparation:

Wood substrate must be sanded using 120, 150 or 180 grit paper prior to staining. On wood such as maple, coarser sanding, such as 150 grit should be performed to avoid polishing of the wood surface. Hand sanding in the direction of the grain following orbital sanding will remove swirl marks. Application must be by hand or spray. The stain must be wiped into the grain and then wiped clean with a clean rag to ensure good adhesion by subsequent clear coats.

General Information:

Product must be thoroughly agitated before use and during application for color consistency. Product can be tinted with 844 Tints up to 25% to achieve dark colors. Dirty and clean rags must be disposed of in a safe and approved manner. The use of closed containers filled with water is the most appropriate way for disposal of the rags. Drying time is fairly short. Only 45 minutes is required prior to apply sealer. However, heavy coats of dark colors should get at least 60 minutes drying. The suggested drying time must be adhered to in order to ensure proper adhesion.

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN IN THIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION

Drying Times:

| | Room Temperature (20°C / 68°F) | Forced Drying Schedule (50°C / 122°F) |
|------------------------|-------------------------------------------|--------------------------------------------------|
| Tack Free Time: | N/A | N/A |
| Dry to Sand: | N/A | N/A |
| Dry to Stack: | N/A | N/A |

Note:

N/A

Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Coatings, Inc
1431 Progress Ave
High Point, NC 27260
336-841-5111

Updated: 2024-05-18 01:00:43

Copyright 2021 AkzoNobel. All Rights Reserved. Chemcraft is a registered trademark of Akzo Nobel Coatings Inc.